

KahlWaxes for the Candle Industry

Product	Wax	DP/MP °C	Acid Val. mgKOH/g	Sap. Val. mgKOH/g	Colour	Shape	Penetration 1/10mm/25 °C
Beeswax yellow	Beeswax 100 % pure	61-65	17-22	87-102	yellow	pellets	-
Beeswax white	Beeswax 100 % pure	61-65	87-104	80-95	white yellowish	pellets	-
8019 yellow	Beeswax	61-65	17-22	87-102	yellow	pellets	-
8019 white	Beeswax	61-65	17-24	87-104	white yellowish	pellets	-
2442	Carnauba Wax pure	82-86	2-7	78-95	pale yellow	flakes	-
1847	Microcrystalline wax, plastic	76-82	-	-	white yellowish	slabs	ca. 28
2868	Microcrystalline wax, soft	74-80	-	-	whitish	slabs	ca. 75
9317	Wax blend	62-68	-	-	off white	drums	ca. 50
2993	Polyolefin wax	65-75	-	-	off white	pellets	ca. 5