

## KahlWaxes for the Polish Industry

Product	Wax	MP/DP °C	Acid Val. mgKOH/g	Sap. Val. mgKOH/g	Colour	Shape
2442	Carnauba wax	82-86	2-7	78-95	light yellow	flakes
6642	Carnauba wax, premium	82-86	2-7	78-95	light yellow	pellets
5026	Carnauba wax	80-86	5-15	80-95	yellow	pellets
1540	Beeswax bleached technical	61-65	17-24	87-104	white	pellets
6740	Montan wax natural, alternative	80-86	5-15	80-95	yellow	pellets
6090	Montan wax bleached	80-86	45-55	130-155	light yellow	flakes
ESL	Montan wax bleached	80-86	28-38	135-155	light yellow	flakes
OP	Montan wax bleached, part. saponified	99-105	7-14	110-130	yellow	flakes, powder
S	Montanic acid	81-87	130-150	155-180	light yellow	flakes
4180	Hydrocarbon wax synthetic	106-114	-	-	white	flakes
2851	Microcrystalline wax	89-95	ca.10 **	-	white	prills
1847	Microcrystalline wax	76-82	ca. 28 **	-	white- yellowish	slabs
2336	Hardwax partially saponified	104-109	less 10	less 10	whitish	flakes
1578	Polyethylene wax	101-109	-	-	opaque- whitish	pellets
4035	Selfgloss wax, selfemulsifying	74-80	2-8	25-30	yellow	flakes
4048	Selfgloss wax, selfemulsifying	77-83	4-10	44-55	yellow	flakes
4091	Selfgloss wax, selfemulsifying	80-86	10-20	75-95	yellow	flakes
4005	Selfgloss wax, selfemulsifying	75-81	20-35	55-75	yellow	flakes
7453	Ethoxilated fatty alcohols	28-33*	-	-	whitish	drums

\* Congealing point

\*\* Penetration (25°C 1/10 mm)